

PBM18Y

Code(d) **596387**

Code(e) **599385**

Refractive Index n_d	1.59551 1.595509	Abbe Number ν_d	38.7 38.77	Dispersion n_F-n_C	0.01537 0.015361
Refractive Index n_e	1.599153	Abbe Number ν_e	38.50	Dispersion $n_F-n_{C'}$	0.015561

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.56207
n_{1970}	1.97009	1.56696
n_{1530}	1.52958	1.57243
n_{1129}	1.12864	1.57779
n_t	1.01398	1.57975
n_s	0.85211	1.58338
$n_{A'}$	0.76819	1.58599
n_r	0.70652	1.58846
n_C	0.65627	1.59097
$n_{C'}$	0.64385	1.59169
$n_{\text{He-Ne}}$	0.6328	1.59236
n_D	0.58929	1.59537
n_d	0.58756	1.59551
n_e	0.54607	1.59915
n_F	0.48613	1.60634
$n_{F'}$	0.47999	1.60725
$n_{\text{He-Cd}}$	0.44157	1.61400
n_g	0.435835	1.61520
n_h	0.404656	1.62284
n_i	0.365015	1.63656
n_{334}	0.334148	1.65255
n_{326}	0.326106	1.65795

Partial Dispersions	
n_C-n_t	0.011228
$n_C-n_{A'}$	0.004982
n_d-n_C	0.004534
n_e-n_C	0.008178
n_g-n_d	0.019689
n_g-n_F	0.008862
n_h-n_g	0.007643
n_i-n_g	0.021360
n_C-n_t	0.011940
$n_e-n_{C'}$	0.007466
n_F-n_e	0.008095
$n_i-n_{F'}$	0.029310

Relative Partial Dispersions	
$\theta_{C,t}$	0.7309
$\theta_{C,A'}$	0.3243
$\theta_{d,C}$	0.2952
$\theta_{e,C}$	0.5324
$\theta_{g,d}$	1.2818
$\theta_{g,F}$	0.5769
$\theta_{h,g}$	0.4976
$\theta_{i,g}$	1.3905
$\theta'_{C,t}$	0.7673
$\theta'_{e,C'}$	0.4798
$\theta'_{F,e}$	0.5202
$\theta_{i,F}$	1.8836

Thermal Properties	
Strain Point StP (°C)	377
Annealing Point AP (°C)	419
Transformation Temperature Tg (°C)	441
Yield Point At (°C)	478
Softening Point SP (°C)	565
Expansion Coefficients (-30~+70°C)	88
α (10 ⁻⁷ /°C) (+100~+300°C)	100
Thermal Conductivity k (W/m·K)	0.865

Coloring			
λ_{80}	340	λ_5	315

Internal Transmittance		
$\lambda(\text{nm})$	τ 10mm	τ 25mm
240		
250		
260		
270		
280		
290		
300		
310		
320	0.22	0.02
330	0.68	0.39
340	0.912	0.79
350	0.975	0.939
360	0.990	0.976
365	0.993	0.983
370	0.995	0.988
380	0.997	0.992
390	0.998	0.994
400	0.998	0.995
420	0.998	0.996
440	0.999	0.997
460	0.999	0.997
480	0.999	0.998
500	0.999	0.998
550	0.999	0.998
600	0.999	0.998
650	0.999	0.998
700	0.999	0.998
800	0.999	0.998
900	0.999	0.998
1000	0.998	0.996
1200	0.998	0.996
1400	0.996	0.990
1600	0.994	0.986
1800	0.979	0.948
2000	0.956	0.89
2200	0.907	0.78
2400	0.87	0.71

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0023
$\Delta\theta_{C,A'}$	0.0015
$\Delta\theta_{g,d}$	-0.0024
$\Delta\theta_{g,F}$	-0.0018
$\Delta\theta_{i,g}$	-0.0099

Mechanical Properties	
Young's Modulus E (10 ⁹ N/m ²)	598
Rigidity Modulus G (10 ⁹ N/m ²)	244
Poisson's Ratio σ	0.223
Knoop Hardness Hk[Class]	410 4
Abrasion Aa	132
Photoelastic Constant β (nm/cm/10 ⁵ Pa)	2.79

Constants of Dispersion Formula *1	
A ₁	1.34660215E+00
A ₂	1.36322343E-01
A ₃	1.83371587E-01
B ₁	1.06313733E-02
B ₂	4.91403013E-02
B ₃	2.39154655E+01

*1 By using these contents, refractive indices for any wavelength between 326 and 1129nm can be calculated. When calculating refractive indices for any wavelength between 1129 and 2325nm, please refer to us.

Other Properties	
Bubble Quality Group B	
Specific Gravity d	3.37
Remarks	

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	2
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	2.0

Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	dn/dt relative (10 ⁻⁶ /°C)								
	t	C'	He-Ne	D	e	F'	g	i	
-40~20	2.5	3.1	3.2	3.4	3.7	4.4	5.2	7.6	
-20~ 0	2.5	3.3	3.3	3.5	3.9	4.6	5.4	7.9	
0~20	2.6	3.4	3.4	3.7	4.0	4.7	5.5	8.1	
20~40	2.7	3.5	3.5	3.8	4.1	4.9	5.7	8.4	
40~60	2.8	3.6	3.6	3.9	4.2	5.0	5.9	8.7	
60~80	2.8	3.7	3.7	4.0	4.3	5.2	6.1	8.9	