

S-BAL12

Code(d) **540595**

Code(e) **542592**

Refractive Index n_d	1.53996 1.539956	Abbe Number ν_d	59.46	Dispersion n_F-n_C	0.009081
Refractive Index n_e	1.542121	Abbe Number ν_e	59.20	Dispersion n_F-n_C'	0.009158

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.51358
n_{1970}	1.97009	1.51848
n_{1530}	1.52958	1.52370
n_{1129}	1.12864	1.52825
n_t	1.01398	1.52974
n_s	0.85211	1.53230
$n_{A'}$	0.76819	1.53404
n_r	0.70652	1.53562
n_C	0.65627	1.53719
$n_{C'}$	0.64385	1.53763
$n_{\text{He-Ne}}$	0.6328	1.53804
n_D	0.58929	1.53988
n_d	0.58756	1.53996
n_e	0.54607	1.54212
n_F	0.48613	1.54627
$n_{F'}$	0.47999	1.54679
$n_{\text{He-Cd}}$	0.44157	1.55056
n_g	0.435835	1.55122
n_h	0.404656	1.55532
n_i	0.365015	1.56232

Constants of Dispersion Formula	
A_1	7.14605258E-01
A_2	6.21993289E-01
A_3	1.22537681E+00
B_1	3.01763913E-03
B_2	1.66505450E-02
B_3	1.43506314E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	1
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	2.0

Mechanical Properties	
Young's Modulus E (10^9N/m^2)	710
Rigidity Modulus G (10^9N/m^2)	306
Poisson's Ratio σ	0.161
Knoop Hardness Hk[Class]	520 5
Abrasion Aa	112
Photoelastic Constant β nm/(cm · 10^5Pa)	2.60

Partial Dispersions	
n_C-n_t	0.007456
$n_C-n_{A'}$	0.003156
n_d-n_C	0.002762
n_e-n_C	0.004927
n_g-n_d	0.011260
n_g-n_F	0.004941
n_h-n_g	0.004105
n_i-n_g	0.011107
n_C-n_t	0.007896
$n_e-n_{C'}$	0.004487
n_F-n_e	0.004671
$n_i-n_{F'}$	0.015531

Relative Partial Dispersions	
$\theta_{C,t}$	0.8211
$\theta_{C,A'}$	0.3475
$\theta_{d,C}$	0.3042
$\theta_{e,C}$	0.5426
$\theta_{g,d}$	1.2400
$\theta_{g,F}$	0.5441
$\theta_{h,g}$	0.4520
$\theta_{i,g}$	1.2231
$\theta'_{C,t}$	0.8622
$\theta'_{e,C'}$	0.4900
$\theta'_{F,e}$	0.5100
$\theta'_{i,F'}$	1.6959

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	-0.0046
$\Delta\theta_{C,A'}$	-0.0005
$\Delta\theta_{g,d}$	-0.0012
$\Delta\theta_{g,F}$	-0.0012
$\Delta\theta_{i,g}$	-0.0040

Thermal Properties	
Strain Point StP (°C)	432
Annealing Point AP (°C)	468
Transformation Temperature Tg (°C)	478
Yield Point At (°C)	527
Softening Point SP (°C)	624
Expansion Coefficients (-30~+70°C)	86
α ($10^{-7}/^\circ\text{C}$) (+100~+300°C)	102
Thermal Conductivity λ W/(m·K)	0.982

Coloring			
λ_{80}	330	λ_5	300
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	330	$\lambda_{0.05}$	301

CCI		
B	G	R
0.00	0.09	0.06

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	0.02
310	0.23
320	0.57
330	0.80
340	0.914
350	0.959
360	0.979
370	0.989
380	0.992
390	0.995
400	0.997
420	0.997
440	0.997
460	0.997
480	0.998
500	0.999
550	0.999
600	0.999
650	0.998
700	0.999
800	0.999
900	0.999
1000	0.999
1200	0.999
1400	0.993
1600	0.995
1800	0.983
2000	0.966
2200	0.920
2400	0.89

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n/\Delta T$ relative ($10^{-6}/^\circ\text{C}$)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	1.4	1.7	1.8	1.8	2.0	2.3	2.6
-20~ 0	1.4	1.7	1.8	1.9	2.0	2.3	2.6
0~20	1.4	1.7	1.8	1.9	2.0	2.3	2.7
20~40	1.4	1.7	1.8	1.9	2.0	2.4	2.7
40~60	1.4	1.7	1.8	1.9	2.1	2.4	2.8
60~80	1.4	1.8	1.8	1.9	2.1	2.4	2.8

Other Properties	
Bubble Quality Group B	
Specific Gravity d	2.75
Remarks	

OHARA 17-04

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.