

S-LAL18

Code(d) **729547**

Code(e) **732544**

Refractive Index n_d	1.72916 1.729157	Abbe Number ν_d	54.68	Dispersion n_F-n_C	0.013335
Refractive Index n_e	1.732336	Abbe Number ν_e	54.45	Dispersion $n_F-n_{C'}$	0.013449

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.68936
n_{1970}	1.97009	1.69701
n_{1530}	1.52958	1.70504
n_{1129}	1.12864	1.71190
n_t	1.01398	1.71411
n_s	0.85211	1.71790
$n_{A'}$	0.76819	1.72046
n_r	0.70652	1.72279
n_C	0.65627	1.72510
$n_{C'}$	0.64385	1.72575
n_{He-Ne}	0.6328	1.72635
n_D	0.58929	1.72904
n_d	0.58756	1.72916
n_e	0.54607	1.73234
n_F	0.48613	1.73844
$n_{F'}$	0.47999	1.73920
n_{He-Cd}	0.44157	1.74473
n_g	0.435835	1.74570
n_h	0.404656	1.75173
n_i	0.365015	1.76203

Constants of Dispersion Formula	
A_1	1.50276318E+00
A_2	4.30224497E-01
A_3	1.34726060E+00
B_1	1.45462356E-02
B_2	-3.32784153E-03
B_3	9.33508342E+01

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	4
Weathering Resistance(Surface) Group W(S)	1
Acid Resistance(Surface) Group SR	51.2
Phosphate Resistance PR	2.0

Mechanical Properties	
Young's Modulus E (10^9N/m^2)	1204
Rigidity Modulus G (10^9N/m^2)	467
Poisson's Ratio σ	0.289
Knoop Hardness Hk[Class]	720 7
Abrasion Aa	69
Photoelastic Constant β nm/(cm· 10^5Pa)	1.58

Partial Dispersions	
n_C-n_t	0.010994
$n_C-n_{A'}$	0.004641
n_d-n_C	0.004056
n_e-n_C	0.007235
n_g-n_d	0.016539
n_g-n_F	0.007260
n_h-n_g	0.006035
n_i-n_g	0.016335
n_C-n_t	0.011640
$n_e-n_{C'}$	0.006589
n_F-n_e	0.006860
$n_i-n_{F'}$	0.022835

Relative Partial Dispersions	
$\theta_{C,t}$	0.8244
$\theta_{C,A'}$	0.3480
$\theta_{d,C}$	0.3042
$\theta_{e,C}$	0.5426
$\theta_{g,d}$	1.2403
$\theta_{g,F}$	0.5444
$\theta_{h,g}$	0.4526
$\theta_{i,g}$	1.2250
$\theta'_{C,t}$	0.8655
$\theta'_{e,C'}$	0.4899
$\theta'_{F',e}$	0.5101
$\theta'_{i,F'}$	1.6979

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0212
$\Delta\theta_{C,A'}$	0.0058
$\Delta\theta_{g,d}$	-0.0109
$\Delta\theta_{g,F}$	-0.0086
$\Delta\theta_{i,g}$	-0.0422

Thermal Properties	
Strain Point StP (°C)	632
Annealing Point AP (°C)	655
Transformation Temperature Tg (°C)	685
Yield Point At (°C)	699
Softening Point SP (°C)	731
Expansion Coefficients (-30~+70°C)	59
α ($10^{-7}/^\circ\text{C}$) (+100~+300°C)	69
Thermal Conductivity λ W/(m·K)	0.871

Coloring			
λ_{80}	365	λ_5	280
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	343	$\lambda_{0.05}$	281

CCI		
B	G	R
0.00	0.30	0.31

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	0.04
290	0.21
300	0.30
310	0.32
320	0.55
330	0.68
340	0.78
350	0.86
360	0.912
370	0.946
380	0.967
390	0.978
400	0.984
420	0.991
440	0.994
460	0.996
480	0.997
500	0.998
550	0.999
600	0.998
650	0.999
700	0.999
800	0.998
900	0.998
1000	0.997
1200	0.996
1400	0.991
1600	0.991
1800	0.982
2000	0.956
2200	0.87
2400	0.60

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n/\Delta T$ relative ($10^{-6}/^\circ\text{C}$)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	3.3	3.7	3.7	3.8	4.0	4.4	4.7
-20~ 0	3.3	3.7	3.7	3.9	4.0	4.4	4.8
0~20	3.3	3.7	3.8	3.9	4.1	4.5	4.9
20~40	3.3	3.8	3.8	4.0	4.1	4.5	5.0
40~60	3.4	3.8	3.9	4.0	4.2	4.6	5.1
60~80	3.5	4.0	4.0	4.1	4.3	4.8	5.2

Other Properties	
Bubble Quality Group B	
Specific Gravity d	4.18
Remarks	

OHARA 18-04

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.