

S-NBM52

Code(d) **622411**

Code(e) **626408**

Refractive Index n_d	1.62205 1.622050	Abbe Number ν_d	41.08	Dispersion n_F-n_C	0.015143
Refractive Index n_e	1.625645	Abbe Number ν_e	40.84	Dispersion $n_F-n_{C'}$	0.015320

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.58373
n_{1970}	1.97009	1.59030
n_{1530}	1.52958	1.59737
n_{1129}	1.12864	1.60375
n_t	1.01398	1.60592
n_s	0.85211	1.60980
$n_{A'}$	0.76819	1.61250
n_r	0.70652	1.61501
n_C	0.65627	1.61754
$n_{C'}$	0.64385	1.61825
$n_{\text{He-Ne}}$	0.6328	1.61892
n_D	0.58929	1.62192
n_d	0.58756	1.62205
n_e	0.54607	1.62564
n_F	0.48613	1.63268
$n_{F'}$	0.47999	1.63357
$n_{\text{He-Cd}}$	0.44157	1.64014
n_g	0.435835	1.64130
n_h	0.404656	1.64868
n_i	0.365015	1.66182

Constants of Dispersion Formula	
A_1	1.39799204E+00
A_2	1.72238041E-01
A_3	1.21742991E+00
B_1	9.46113686E-03
B_2	4.44077736E-02
B_3	1.05313930E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	3
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E (GPa)	80.8
Rigidity Modulus G (GPa)	32.5
Poisson's Ratio σ	0.243
Knoop Hardness Hk(Class)	540 5
Abrasion Aa	120

Partial Dispersions	
n_C-n_t	0.011617
$n_C-n_{A'}$	0.005036
n_d-n_C	0.004511
n_e-n_C	0.008106
n_g-n_d	0.019249
n_g-n_F	0.008617
n_h-n_g	0.007384
n_i-n_g	0.020524
n_C-n_t	0.012329
$n_e-n_{C'}$	0.007394
$n_{F'}-n_e$	0.007926
$n_i-n_{F'}$	0.028252

Relative Partial Dispersions	
$\theta_{C,t}$	0.7672
$\theta_{C,A'}$	0.3326
$\theta_{d,C}$	0.2979
$\theta_{e,C}$	0.5353
$\theta_{g,d}$	1.2711
$\theta_{g,F}$	0.5690
$\theta_{h,g}$	0.4876
$\theta_{i,g}$	1.3553
$\theta'_{C,t}$	0.8048
$\theta'_{e,C'}$	0.4826
$\theta'_{F',e}$	0.5174
$\theta'_{i,F'}$	1.8441

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0278
$\Delta\theta_{C,A'}$	0.0070
$\Delta\theta_{g,d}$	-0.0083
$\Delta\theta_{g,F}$	-0.0060
$\Delta\theta_{i,g}$	-0.0257

Thermal Properties	
Strain Point StP (°C)	541
Annealing Point AP (°C)	568
Transformation Temperature Tg (°C)	584 *
Yield Point At (°C)	645 *
Softening Point SP (°C)	701
Expansion Coefficients (-30~+70°C)	74 *
α (10 ⁻⁷ K ⁻¹) (+100~+300°C)	87 *
Thermal Conductivity λ W/(m·K)	0.957

Coloring			
λ_{80}	355	λ_5	320
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	346	$\lambda_{0.05}$	320

CCI		
B	G	R
0.00	0.24	0.25

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	
320	0.04
330	0.33
340	0.69
350	0.86
360	0.933
370	0.962
380	0.976
390	0.984
400	0.989
420	0.993
440	0.994
460	0.996
480	0.997
500	0.998
550	0.999
600	0.999
650	0.999
700	0.999
800	0.999
900	0.999
1000	0.999
1200	0.999
1400	0.984
1600	0.991
1800	0.984
2000	0.967
2200	0.87
2400	0.75

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n / \Delta T$ relative (10 ⁻⁶ K ⁻¹)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	2.7	3.2	3.2	3.4	3.6	4.1	4.7
-20~ 0	2.7	3.3	3.3	3.5	3.7	4.2	4.9
0~20	2.7	3.3	3.3	3.5	3.8	4.3	5.0
20~40	2.7	3.3	3.3	3.5	3.8	4.4	5.0
40~60	2.8	3.4	3.4	3.6	3.9	4.5	5.2
60~80	3.0	3.6	3.6	3.8	4.1	4.7	5.4

Other Properties	
Photoelastic Constant β nm/(cm·10 ⁵ Pa)	3.62
Specific Gravity d	2.86
Remarks	

OHARA 24-01

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.